

## ILVA TECHNICAL DATA SHEET

**PRODUCTS SERIES:** KLIMA SERIES

**PRODUCT CODE:** PN4B

**DESCRIPTION:** **KLIMA AQUATECH PIGMENTED THIXOTROPIC SEALER - WHITE**  
This product is a thixotropic filling sealer based on water-based one-component acrylic resins in water dispersion for wood protection. Allows application of high product thickness in only one-coat, without risk of sagging.

**PRODUCT PREPARATION:** PN4B WB Exterior Primer 100 parts by weight or volume  
Water Thinner 5 parts by weight or 6 parts by volume

**USES:** For outdoor use. Suitable for hardwoods and softwoods.

**APPLICATION SYSTEM:** Brush, spray (air, airmix, airless). If airless spray we recommend diluting 3-5% to help air release during film-forming. For best results use Kremlin 30:1 pump with Aurmix 600 fluid lbs, 35-40 static atomizing air 06134/06154

**FILM THICKNESS:** 8-10 mils wet film

**COATS:** One or two depending on desired build

**GENERAL PROPERTIES:** Specific Gravity, gr/cc 1.20+/- .02  
Viscosity (Brookfield aspd 4 vel.2) 25,000 cps  
Solids, % by weight: 51 +/-2

**DRYING TIME:** Air drying (at room temperature with good ventilation)  
Dry to touch 20 minutes  
Dry to sand: 2 hours  
Dry to handle: 12-16 hours  
Tunnel (35-40°C, 95-104°F) 90 minutes  
(Drying times will vary according to temperature, ventilation and relative humidity)

**COATING CYCLES:** Cycle 1 - Pigmented Coating Cycle with Thixotropic Topcoat - White  
Substrate: Non-bleeding softwoods and hardwoods  
Wood Preservative: 1 coat of PN410, TN340 or TN30  
Sealer 1 coat of PN4B reduced with water -4 hours before sanding  
Sanding Sand using 320 grit stearedated paper. Avoid high pressure or reduce speed on powered sanding equipment to avoid overheating the waterbase product and loading up sandpaper.  
Topcoat 1 coat of PN6B reduced with water -4 hours drying

**PRODUCT PROPERTIES:** PN 4B sealer is characterized by very good hiding and filling capacity. Highly flexible following dimensional moves of the wood without flaking off. Easy maintenance.

**MAINTENANCE:** Finished items should be lightly sanded with 240 or 320 grit and recoated or topcoated with 1 or 2 coats of PN6B.

**WARNINGS:** KEEP FROM FREEZING!

**SHELF LIFE:** 12 Months

**STORAGE:** Store in a tightly closed container at room temperatures (18 -25 °C/64 -75 °F) and protect from moisture and foreign material. Do not store at temperatures below 7°C (45°F).

**DATE OF ISSUANCE:** 03-13, 7-16, 2-18

**IC & S, P.O. BOX 10845, LANCASTER, PA 17605  
(800) 220-4035**

EVERY REASONABLE PRECAUTION IS TAKEN IN THE MANUFACTURE OF OUR PRODUCTS TO INSURE THAT THEY COMPLY WITH OUR STANDARDS. INFORMATION GIVEN IS CORRECT TO THE BEST OF OUR KNOWLEDGE. ANY SUGGESTIONS MADE BY US COVERING THE USE OF OUR PRODUCTS ARE BASED ON EXPERIENCE AND/OR TESTS BELIEVED TO BE RELIABLE. HOWEVER, BECAUSE THE USE OF ANY PRODUCT OF OUR MANUFACTURE IS COMPLETELY BEYOND OUR CONTROL, INCLUDING FOR EXAMPLE, THE METHOD AND CONDITIONS OF APPLICATION, NO GUARANTEE OR WARRANTY, EXPRESSED OR IMPLIED, IS MADE. MANUFACTURER'S MAXIMUM LIABILITY SHALL BE TO REPLACE SUCH QUANTITY OF PRODUCT DETERMINED BY OUR LABORATORY TO BE DEFECTIVE. USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR HIS INTENDED USE AND ASSUME ALL RISK AND LIABILITY IN CONNECTION THEREWITH.